



**Conductive PU Foam Sheet
1104-0006**

Physical Properties

Raw Material	Carbon, Polyurethane	
Density	0.082	g / cm ³
Tensile Strength	10.4	psi
Elongation	170	%
Tear	2.1	Lbs/in
Flexural Modulus	520	kgf / cm ²
Brittle Point	-75	°C
Surface Resistivity	10E3 - 10 E5	Ohm / sqmt
Thickness	0.8	mm

05 November 2018 (ME02)