



**Conductive PE Foam Sheet
AE-150**

Physical Properties

Density	0.066	g / cm ³
Tensile Strength	0.82, 8.4	Mpa, kgf / cm ²
Elongation	80	%
Breaking Power	34, 3.5	N/cm, kgf / cm ²
Compressed Hardness	0.098, 1	Mpa, kgf / cm ²
25% Permanent Compressed %	2.4	%
Degree of Temperature Change (70 °C x 22 Hr)	-0.6	%
Absorbability (B Method)	0.001	g / cm ³
Surface Resistance	Less than 2.7 x 10 ⁵	Ohm / sq