



**Pink Antistatic PE Foam
1403 Series**

Electrical Properties

Static Decay Test (From 5000V to 1% at 73°F, 12% RH)	< 2	Sec	Method 4046 ASTM D 257
--	-----	-----	------------------------

Surface Resistivity	10 ¹¹	ohm/sq	Method 4046* ASTM D 257
---------------------	------------------	--------	-------------------------

Physical Properties

Compressive Deflection at (Vertical Direction) 10%	1.5	psi	ASTM D3575 TEST B
--	-----	-----	-------------------

Compressive Deflection at (Vertical Direction) 25%	4.4	psi	ASTM D3575 TEST B
--	-----	-----	-------------------

Compressive Deflection at (Vertical Direction) 50%	14.5	psi	ASTM D3575 TEST B
--	------	-----	-------------------

Tensile Strength (Machine Direction)	32	Ps	ASTM D638
--------------------------------------	----	----	-----------

Elongation at Break	< 100	%	ASTM D638
---------------------	-------	---	-----------

Tear Resistance (Machine Direction)	9.2	lb/in	ASTM 1004
-------------------------------------	-----	-------	-----------

Density Range	1.7	pcf	ASTM D3575 TEST C METHOD B
---------------	-----	-----	-------------------------------

Thermal Conductivity at 75 ° F	0.35 - 0.45	BTU-in/hr.ft2	ASTM D3575 TEST E METHOD B
--------------------------------	-------------	---------------	-------------------------------

05 November 2018 (AS01)