



**Amide Free LDPE Bag
1608 Series**

Feature	Benefit
Transparent	Identified product been packed
Non corrosive, no amides, silicon, chloride or Sulphate	Will not affect metal part

Physical Properties

Density	0.922	g/cu.cm	ASTM D1505
Tensile Strength at break	160	Kg/sq.cm	ASTM D638
Elongation	600	%	ASTM D638
Flexural Modulus	2200	Kg/sq.cm	ASTM D747
Meeting Point	110	°C	-

05 November 2018 (AS01)